



Inhibition effects of a DMPO derivative on the corrosion of zinc-aluminium alloy in 0.1N Hydrochloric acid solution by OCP method at different temperatures

R.D.Pruthviraj

R&D Centre, Department of Chemistry, RajaRajeswari College of Engineering, Bangalore, Karnataka, (INDIA)

E-mail: pruthvirajrd@gmail.com

ABSTRACT

1,5-Dimethyl-4-((2-methylbenzylidene)amino)-2-phenyl-1H-pyrazol-3(2H)-one (DMPO) was synthesized to be evaluated as a corrosion inhibitor. The corrosion inhibitory effects of DMPO on Zinc-Aluminum alloy in 1.0 M HCl were investigated using open circuit potential (OCP). The results showed that DMPO inhibited Zinc-Aluminium alloy corrosion in acid solution and indicated that the inhibition efficiency increased with increasing inhibitor concentration. Changes in the impedance parameters suggested an adsorption of DMPO onto the Zinc-Aluminum Alloy surface, leading to the formation of protective films. The novel synthesized corrosion inhibitor was characterized using UV-Vis spectral analyses.

© 2016 Trade Science Inc. - INDIA

KEYWORDS

Corrosion inhibitor;
Open circuit potential
(OCP) and DMPO.


INTRODUCTION

Corrosion inhibitors are of considerable practical importance, as they are extensively employed in reducing metallic waste during production and in minimizing the risk of material failure, both of which can result in the sudden shut-down of industrial processes, which in turn leads to added costs^[1]. It is also important to use corrosion inhibitors to prevent metal dissolution and minimize acid consumption^[2-4]. The majority of well-known acid inhibitors are organic compounds that contain nitrogen, sulfur and oxygen atoms. The inhibitory action exercised by organic compounds on the dissolution of metallic species is normally related to adsorption interactions between the inhibitors and

the metal surface^[5,6]. The planarity (p) and lone pairs of electrons present on N, O and S atoms are important structural features that control the adsorption of these molecules onto the surface of the metal. The purpose of this work was to verify the previously established results on the corrosion inhibition effect of various Schiff bases on Aluminum Alloy in acidic media^[7]. Many researchers have reported that the inhibition effect depends mainly on some physicochemical and electronic properties of the organic inhibitor related to its functional groups, steric effects, electronic density of donor atoms and orbital character of electrons donor^[8]. Schiff bases are organic compounds that have the general formula $R-C=N-R-$, where R and R- are aryl, alkyl or heterocyclic groups. Schiff bases are formed by the

Full Paper

condensation reaction of a primary amine and a ketone or aldehyde and are potential corrosion inhibitors. The greatest advantage of many Schiff base compounds is that they can be conveniently and easily synthesized from relatively cheap materials. Due to the presence of the imine group ($-C=N-$) and electronegative nitrogen, sulfur and/or oxygen atoms in the molecule, Schiff bases have been reported to be effective inhibitors for the corrosion of steel in acid media by several authors^[9-12]. Conversely, the surface state and excess charge of the metal have also been reported to affect the adsorption behavior of inhibitor molecules onto the metal surface^[13]. Generally, the tendency to form a stronger coordination bond, consequently resulting in high inhibition efficiency, increases in the order of $O < N < S < P$ ^[14]. As a continuation of previous studies^[15-20], we focused on the synthesis of new heterocyclic compounds as novel organic corrosion inhibitors. Herein, we report the synthesis of 1, 5-dimethyl-4-((2-methylbenzylidene) amino)-2-phenyl-1H-pyrazol-3(2H)-one, DMPO, and chemical structure elucidation using spectroscopic techniques *i.e.*, UV-Vis. Recent studies have shown that organic compounds containing polar functional groups are quite efficient in minimizing the effect of corrosion in addition to heterocyclic compounds containing polar groups and π -electrons. The molecular design of the DMPO molecule is based on the fact that 4-aminoantipyrine consists of amine, methylamine, carbonyl and π -electron bonds, which would effectively contribute towards the inhibition of Zinc-Aluminium Alloy corrosion in acidic media. Moreover, Schiff bases containing imine groups would contribute more effectively to the inhibition of corrosion of Zinc-Aluminium alloy in acid medium. The proposed structure of the synthesized novel corrosion inhibitor is shown in below.




Chemical structure of 1, 5-dimethyl-4-((2-methylbenzylidene) amino)-2-phenyl-1H-pyrazol-3(2H)-one (DMPO).


EXPERIMENTAL SECTION

All chemicals used were of reagent grade (supplied by Sigma-Aldrich) and used as supplied



EC DoubleBeam UV-VIS Spectrophotometer
 Date : 08/28/15 Time : 15:56:14
 System : ECIL UV 5704as
 Sample_ID : venkatesh T
 Analyst : DMPO
 File Name : DMPO.abs





Spectrophotometer Uv 5704SS

Synthesis of corrosion inhibitor DMPO

To synthesize the new corrosion inhibitor DMPO, the reaction sequence outlined in was followed, starting from commercially available 4-aminoantipyrine. The synthesis was carried out by refluxing 4-aminoantipyrine with 2-methylbenzaldehyde in the presence of a few drops of acetic acid. The mechanism of this reaction followed the Schiff base mechanism.

A solution of 2-methylbenzaldehyde (0.4 mmol) in 50 mL ethanol was refluxed with 4-aminoantipyrine (0.4 mmol) for 5 h. After cooling to room temperature, a solid mass was separated and recrystallized from ethanol in 87% yield




Fig. 1. Open circuit potential studies of Zinc Aluminum Alloy in 0.1N HCl solution using DMPO as an Organic inhibitor @ 25°C




Fig. 3. Open circuit potential studies of Zinc Aluminum Alloy in 0.1N HCl solution using DMPO as an Organic inhibitor @ 35°C

without further purification. Uv-Visible spectra were recorded on a double beam Uv-Vis

Open circuit potential (OCP) measurements




Fig. 2. Open circuit potential studies of Zinc Aluminum Alloy in 0.1N HCl solution using DMPO as an organic inhibitor @ 30°C




Fig. 4. Open circuit potential studies of Zinc Aluminum Alloy in 0.1N HCl solution using DMPO as an organic inhibitor @ 40°C

Full Paper

RESULT AND DISCUSSIONS

The OCP of Zinc-Aluminium Alloy was monitored in the presence of 10ppm, 20 ppm, 30ppm and 50ppm of DMPO. Figure 3 presents the effect of the presence of the DMPO inhibitor on the variation of the OCP of Zinc- aluminium alloy in 1.0 M HCl solutions. This preliminary result suggests that DMPO can retard both reactions under open circuit conditions, including the oxidation of the oxide-free iron and the discharge of the hydrogen ions to produce hydrogen gas on the surface of the Zinc-Aluminium Alloy^[26,27].

Sem after corrosion test




Fig.5. Open circuit potential studies of Zinc Aluminium Alloy in 0.1N HCl solution using DMPO as an Organic inhibitor @ 45°C




Figure 6 : After corrosion test with 20ppm of dmpo inhibitor

CONCLUSIONS

In this study, 1,5-dimethyl-4-((2-




Figure 7 : After corrosion test with 50ppm of dmpo inhibitor




Figure 8 : After corrosion test with 10ppm of dmpo inhibitor

methylbenzylidene) amino)-2- phenyl-1*H*-pyrazol-3(2*H*)-one (DMPO), was sequentially synthesized and characterized using Uv-Vis spectroscopic methods, open circuit potential (OCP) to study the corrosion inhibition of Zinc-aluminium alloy in 1.0 M HCl solutions at different temperature using different concentrations of DMPO as an inhibitor. This compound exhibited excellent inhibition performance as a mixed-type inhibitor. In general, the acidic corrosion of Zinc- aluminium alloy was reduced upon the addition of an appropriate concentration of DMPO. DMPO acts as an efficient corrosion inhibitor in 1.0 M hydrochloric acid.

ACKNOWLEDGMENT

The authors gratefully acknowledge VGST, Govt. of Karnataka for financial support under the project CISEE /2014-15/ GRD No. 325. Also express their gratitude to Management and Principal, RajaRajeswari College of Engineering, Bangalore for providing infrastructural facilities.

REFERENCES

- [1] P.R.Roberge; Handbook of corrosion engineering, McGraw-hill professional publishing, New York, NY, USA, 1999, 1–3 (1999).
- [2] D.N.Sing, A.K.Dey; Synergistic effects of inorganic and organic cations on inhibitive performance of propargyl alcohol on steel dissolution in boiling hydrochloric acid solution, *Corrosion*, **49**, 594–600 (1993).
- [3] G.Banerjee, S.N.Malhotra; Contribution to adsorption of aromatic amines on aluminium alloy surface from HCl solutions by impedance, UV, and raman spectroscopy, *Corrosion*, **48**, 10–15 (1992).
- [4] S.T.Arab, E.A.Noor; Inhibition of acid corrosion of steel by some S-Alkylisothiuronium, *Corrosion*, **49**, 122–129 (1993).
- [5] F.H.Khaled; Investigation of the inhibitive effect of ortho-substituted on corrosion of iron in 0.5 M H₂SO₄ solutions, *Mater.Chem.Phys.*, **82**, 949–960 (2003).
- [6] W.Lin; Inhibiting effect of 2-mercaptopyrimidine on the corrosion of a low carbon steel in phosphoric acid, *Corros.Sci.*, **43**, 1637–1644 (2001).
- [7] H.Shorky, M.Yuasa, I.Sekine, R.M.Issa, H.Y.El-Baradie, G.K.Gomma; Corrosion inhibition of aluminium alloy by schiff base compounds in various aqueous solutions, *Corros.Sci.*, **40**, 2173–2186 (1998).
- [8] M.Abdallah; Rhodanine azosulpha drugs as corrosion inhibitor, *Corros.Sci.*, **44**, 717–728 (2002).
- [9] R.A.Prabhu, T.V.Venkatesha, A.V.Shanbhag, G.M.Kulkarni, R.G.Kalkhambkar; Inhibition effects of some schiff's bases on the corrosion of aluminium alloy in hydrochloric acid solution, *Corros.Sci.*, **50**, 3356–3362 (2008).
- [10] R.A.Prabhu, A.V.Shanbhag, T.V.Venkatesha; Influence of tramadol [2-[(dimethylamino)methyl]-1-(3-methoxyphenyl)cyclohexanolhydrate] on corrosion inhibition of aluminium alloy in acidic media, *J.Appl.Electrochem.*, **37**, 491–497 (2007).
- [11] El M.Naggar; Corrosion inhibition of aluminium alloy in acidic medium by some sulfa drugs compounds, *Corros.Sci.*, **49**, 2226–2236 (2007).
- [12] I.B.Obot, Obi N.O.Egbedi, S.A.Umoren; Drugs as corrosion inhibitors for aluminium in 0.1 M HCl, *Corros.Sci.*, **51**, 1868–1875 (2009).
- [13] S.K.Shukla, M.A.Quraishi; 4-Substituted anilinomethylpropionate: New and efficient, Corrosion inhibitors for aluminium alloy, *Corros.Sci.*, **51**, 1007–1011 (2009).
- [14] S.K.Shukla, A.K.Singh, I.Ahamad, M.A.Quraishi; Drug as corrosion inhibitor for aluminium alloy in hydrochloric acid solution, *Mater.Lett.*, **63**, 819–822 (2009).
- [15] Al A.A.Amiery, Al R.I.Bayati, F.M.Saed, W.B.Ali, A.H.Kadhun, A.B.Mohamad; Novel pyranopyrazoles: Synthesis and theoretical studies, *Molecules*, [PubMed], **17**, 10377–10389 (2012).
- [16] A.A.H.Kadhun, A.Mohamad, Al A.A.Amiery; Antimicrobial and anti-oxidant activities of new metal complexes derived from 3-aminocoumarin, *Molecules*, [PubMed], **16**, 6969–6984 (2011).
- [17] A.A.H.Kadhun, Al A.A.Amiery, M.Shikara, A.Mohamad., Al R.Bayati; Synthesis, Structure elucidation and DFT studies of new thiadiazoles, *Int.J.Phys.Sci.*, **6**, 6692–6697 (2012).
- [18] Al A.A.Amiery; Synthesis and antioxidant, Antimicrobial evaluation, DFT studies of novel metal complexes derivate from Schiff base, *Res.Chem.Intermediat.*, **38**, 745–759 (2012).
- [19] Al A.A.Amiery, A.A.H.Kadhun, A.Mohamad; Antifungal activities of new coumarins, *Molecules*, [PubMed], **17**, 5713–5723 (2012).
- [20] S.Junaedi, A.A.H.Kadhun, Al A.A.Amiery, A.Mohamad, M.Takriff; Synthesis and characterization of novel corrosion inhibitor derived from oleic acid: 2-Amino 5-Oleyl-1,3,4Thiadiazol (AOT), *Int.J.Electrochem.Sci.*, **7**, 3543–3554 (2012).
- [21] A.Y.Musa, A.A.H.Kadhun, A.B.Mohamad, A.R.Daud, M.S.Takriff, S.K.Kamarudin; A comparative study of the corrosion inhibition of aluminium alloy in sulphuric acid by 4,4-dimethylloxazolidine-2-thione, *Corros.Sci.*, **51**, 2393–2399 (2009).
- [22] S.Hleli, A.Abdelghani, A.Tlili; Impedance spectroscopy technique for DNA hybridization, *Sensors*, **3**, 472–479 (2003).
- [23] Z.Wang; The inhibition effect of Bis-Benzimidazole compound for aluminium alloy in 0.5 M HCl solution, *Int.J.Electrochem.Sci.*, **7**, 11149–11160 (2012).
- [24] Ramesh V.Saliyan, A.V.Adhikari; Quinolin-5-ylmethylene-3-[[8-(trifluoromethyl)quinolin-4-yl]thio]propanohydrazide as an effective inhibitor of aluminium alloy corrosion in HCl solution, *Corros.Sci.*, **50**, 55–61 (2008).
- [25] F.G.Liu, M.Du, J.Zhang, M.Qiu; Electrochemical behavior of Q235 steel in saltwater saturated with

Full Paper

- carbon dioxide based on new imidazoline derivative inhibitor, *Corros.Sci.*, **51**, 102–109 (2009).
- [26] De F.S.Souza; Caffeic acid as a green corrosion inhibitor for aluminium alloy, *Corros.Sci.*, **51**, 642–649 (2009).
- [27] A.A.Hermas, M.S.Morad; A comparative study on the corrosion behaviour of 304 austenitic stainless steel in sulfamic and sulfuric acid solutions, *Corros.Sci.*, **50**, 2710–2717 (2008).
- [28] T.Arslan, F.Kandemirli, E.Ebens, I.Love, H.Alemu; Quantum chemical studies on the corrosion inhibition of some sulphonamides on aluminium alloy in acidic medium, *Corros.Sci.*, **51**, 35–47 (2009).
- [29] Obi N.O.Egbedi; Inhibitive properties, thermodynamic and quantum chemical studies of alloxazine on aluminium alloy corrosion in H_2SO_4 , *Corros.Sci.*, **53**, 263–275 (2011).
- [30] Al A.A.Amiery, Al R.Bayati, K.Saour, M.Radi; Cytotoxicity, Antioxidant and antimicrobial activities of novel 2-quinolone derivatives derived from coumarins, *Res.Chem.Intermediat*, **38**, 559–569 (2012).
- [31] Al A.A.Amiery, A.Y.Musa, A.A.H.Kadhun, A.Mohamad; The antioxidant activity of new coumarin derivatives, *Int.J.Mol.Sci.*, **12**, 5757–5761 (2011).
- [32] Al A.A.Amiery, A.A.H.Kadhun, A.Mohamad; Antifungal and antioxidant activities of pyrrolidone-thiosemicarbazone complexes, *Bioinorg.Chem.Appl.*, **2012**, 1–5 (2012).
- [33] Al A.A.Amiery, Al Y.Majedy, H.Abdulreazak, H.Abood; Synthesis, Characterization, Theoretical crystal structure, and antibacterial activities of some transition metal complexes of the thiosemicarbazone, *Bioinorg.Chem.Appl.*, **2011**, 1–6 (2011).
- [34] Al A.A.Amiery; Antimicrobial and antioxidant activities of new metal complexes derived from (*E*)-3-((5-phenyl-1,3,4-oxadiazol-2-ylimino) methyl) naphthalen-2-ol, *Med.Chem.Res.*, **21**, 3204–3213 (2012).
- [35] F.Kandemirli, S.Sagdinc; Theoretical study of corrosion inhibition of amides and thiosemicarbazones, *Corros.Sci.*, **49**, 2118–2130 (2007).
- [36] Al A.A.Amiery, A.Y.Musa, A.A.H.Kadhun, A.Mohamad; The use of umbelliferone in the synthesis of new heterocyclic compounds, *Molecules*, **16**, 6833–6843 (2011).
- [37] J.M.Costa, J.M.Lluch; The use of quantum mechanics calculations for the study of corrosion inhibitors, *Corros.Sci.*, **24**, 924–933 (1984).
- [38] N.Khalil; Quantum chemical approach of corrosion inhibition, *Electrochim.Acta.*, **48**, 2635–2640 (2003).
- [39] G.Bereket, C.Ogretir, A.Yurt; Quantum mechanical calculations on some 4-methyl-5-substituted imidazole derivatives as acidic corrosion inhibitor for zinc, *J.Mol.Struct. (Theochem.)*, **571**, 139–145 (2001).
- [40] S.Xia, M.Qiu, L.Yu, F.Liu, H.Zhao; Molecular dynamics and density functional theory study on relationship between structure of imidazoline derivatives and inhibition performance, *Corros.Sci.*, **50**, 2021–2029 (2008).
- [41] A.Y.Musa, A.H.Kadhun, A.B.Mohamad, A.B.Rahoma, H.Mesmari; Electrochemical and quantum chemical calculations on 4,4-dimethyloxazolidine-2-thione as inhibitor for aluminium alloy corrosion in hydrochloric acid, *J.Mol.Struct.*, **969**, 233–327 (2010).
- [42] I.B.Obot, E.E.Ebenso, I.A.Akpan, Z.M.Gasem, Afolabi S.Ayo; 119Thermodynamic and density functional theory investigation of sulphathiazole as green corrosion inhibitor at aluminium alloy/hydrochloric acid interface, *Int.J.Electrochem.Sci.*, **7**, 1978–1996 (2012).
- [43] I.B.Obot, Obi N.O.Egbedi; Anti-corrosive properties of xanthone on aluminium alloy corrosion in sulphuric acid: Experimental and theoretical investigations, *Curr.Appl.Phys.*, **11**, 382–392 (2011).
- [44] I.B.Obot, Obi N.O.Egbedi, A.O.Eseola; Anticorrosion potential of 2-Mesityl-1*H*-imidazo[4,5-*f*][1,10]phenanthroline on aluminium alloy in sulfuric acid solution: Experimental and theoretical study, *Ind.Eng.Chem.Res.*, **50**, 2098–2110 (2011).
- [45] I.B.Obot, Obi N.O.Egbedi; 1171Theoretical study of benzimidazole and its derivatives and their potential activity as corrosion inhibitors, *Corros.Sci.*, **52**, 657–660 (2010).
- [46] ASTM (American society for testing and materials) Standard practice for preparing, Cleaning, and evaluating corrosion test specimens, ASTM, West Conshohocken, PA, USA, [(accessed on 11 March 2013)], (2003).
- [47] Al A.A.Amiery, A.H.K.Abdul, B.M.Abu, J.Sutiana; A novel hydrazinecarbothioamide as a potential corrosion inhibitor for aluminium alloy in HCl, *Materials*, **6**, 1420–1431 (2013).