



ION EXCHANGE EQUILIBRIUM STUDY USING STRONGLY ACIDIC CATION EXCHANGE RESINS INDION-225

P. U. SINGARE^{*}, R. S. LOKHANDE^a and V. Y. PATTEBAHADUR^b

Department of Chemistry, Bhavan's College, Andheri, MUMBAI – 400058 (M. S.) INDIA

^aDepartment of Chemistry, University of Mumbai, Vidyanagari, Santacruz,
MUMBAI – 400098 (M. S.) INDIA

^bDepartment of Chemistry, Sathaye College, Vile Parle, MUMBAI – 400057 (M. S.) INDIA

ABSTRACT

The study on thermodynamics of ion exchange equilibrium for uni-univalent H^+ / Na^+ , H^+ / K^+ reaction systems were carried out using strongly acidic cation exchange resin Indion-225. For both the uni-univalent ion exchange reaction systems, the equilibrium constant K' were calculated by using Bonner et. al equation by taking into account the mole fraction of ions in the resin phase. The equilibrium constant values calculated for uni-univalent cation exchange reaction systems were observed to increase with rise in temperature, indicating the endothermic exchange reactions having enthalpy values of 27.4 and 13.2 kJ/mol, respectively. On the basis of enthalpy values, the preferential selectivity of ion exchange resins in H^+ form for different univalent ions in aqueous solution is predicted.

Key words: Ion exchange equilibrium, Equilibrium constant, Ionic selectivity, Enthalpy, Endothermic reactions, Indion-225.

INTRODUCTION

Extensive work was done by previous researchers to study the properties of the ion exchange resins, to generate thermodynamic data related to various uni-univalent and heterovalent ion exchange systems¹⁻⁷. Recently, theories explaining ion exchange equilibrium between the resin phase and solution was also developed⁸. A number of researchers carried out equilibrium studies, extending over a wide range of composition of solution and resin phase⁹⁻³¹. Attempts were also made to study the temperature effect on anion exchange systems^{12, 24-31} for computing the thermodynamic equilibrium constants. However, very little work was carried out to study the equilibrium of cation exchange

* Author for correspondence; E-mail: pravinsingare@vsnl.net

systems⁹⁻²³. Therefore, in the present investigation, attempts were made to study the thermodynamics of uni-univalent cation exchange equilibrium, the results of which will be of considerable use in explaining the selectivity of ion exchanger for various bivalent ions in solution.

EXPERIMENTAL

The ion exchange resin Indion-225 as supplied by the manufacturer (Ion Exchange India, Ltd., Mumbai) was a strongly acidic cation exchange resins in H⁺ form containing 8% S-DVB of 16-50 mesh size. For present investigation, the resin grains of 30-40 mesh size were used. The conditioning of the resins was done by usual methods²⁵⁻²⁹.

0.500 g of ion exchange resins in H⁺ form was equilibrated with Na⁺ ion solution of different concentrations at a constant temperature of 30.0 °C for 3 h. From the results of kinetics study reported earlier³²⁻⁴⁴, it was observed that this duration was adequate to attain the ion exchange equilibrium. After 3 h, the different Na⁺ ion solutions in equilibrium with ion exchange resins were analysed for their H⁺ ion concentration by potentiometric titration with standard 0.1N NaOH solution. From the results, the equilibrium constant \mathcal{K} for the reaction was determined at 30.0 °C. The equilibrium constants \mathcal{K} for the above H⁺ / Na⁺ system was determined for different temperatures in the range of 30.0 °C to 40.0 °C.



Similar study was also carried out for H⁺ / K⁺ system in the same temperature range, to study the equilibrium constant \mathcal{K} for the reaction



The sodium and potassium ion solutions used in the entire experimental work, were prepared by dissolving potassium and sodium chloride salts (Analytical grade) in distilled deionised water. In the present study, a semi-micro burette having an accuracy of 0.05 mL was used in the titrations and the titration readings were accurate to ± 0.05 mL. Considering the magnitude of the titer values, the average equilibrium constants reported in the experiment are accurate to ± 3 %.

RESULTS AND DISCUSSION

The equilibrium constants for the uni-univalent ion exchange reactions (1 and 2) would be given by the expression

$$K = \frac{C_{RX} \cdot C_H^+}{(A - C_{RX}) \cdot C_x^+} \quad \dots(3)$$

Here A is the ion exchange capacity of the resin; x^+ represents Na^+ or K^+ ions. For different concentrations of x^+ ions in solution at a given temperature, K values were calculated from which average value of K for that set of experiment was calculated (Tables 1 and 3). Similar values of K were calculated for both H^+/K^+ and H^+/Na^+ systems for different temperatures (Table 5).

Table 1: Equilibrium constant for the ion exchange reaction




Amount of the ion exchange resin in H^+ form = 0.500 g,

Ion exchange capacity = 3.34 meq. / g,

Volume of K^+ ion solution = 80.0 mL, Temperature = 30.0 °C

System	Initial conc. of K^+ ion (M)	Final conc. of K^+ ions (M) C_{K^+}	Change in K^+ ion conc.	Conc. of H^+ ions exchanged (M) C_{H^+}	Amount of K^+ ions exchanged on the resin meq. / 0.5 g C_{RK}	Equilibrium constant K
1	0.010	0.005	0.005	0.005	0.256	0.087
2	0.020	0.011	0.009	0.009	0.438	0.117
3	0.025	0.015	0.010	0.010	0.494	0.113
4	0.030	0.020	0.010	0.010	0.513	0.094
5	0.040	0.028	0.012	0.012	0.588	0.089

Average equilibrium constant (K) = 0.100

Table 2 : Equilibrium constant for the ion exchange reaction


Amount of the ion exchange resin in H^+ form = 0.500 g,

Ion exchange capacity = 3.34 meq. / g,

Volume of K^+ ion solution = 80.0 mL, Temperature = 30.0 °C

System	Initial conc. of K^+ ions in solution (M)	Final conc. of K^+ ions in solution (M) m_{K^+}	Conc. of H^+ ions exchanged in solution (M) m_{H^+}	Mole fraction of K^+ ions exchanged on the resin N_{K^+}	Mole fraction of H^+ ions remained on the resin N_{H^+}	Equilibrium Constant K'
1	0.01	0.005	0.005	0.077	0.923	0.087
2	0.02	0.011	0.009	0.131	0.869	0.117
3	0.025	0.015	0.010	0.148	0.852	0.113
4	0.03	0.020	0.010	0.153	0.847	0.094
5	0.04	0.028	0.012	0.176	0.824	0.089

Average equilibrium constant (K') = 0.100

Table 3 : Equilibrium constant for the ion exchange reaction

Amount of the ion exchange resin in H^+ form = 0.500 g,

Ion exchange capacity = 3.38 meq. / g,

Volume of Na^+ ion solution = 80.0 mL,

Temperature = 30.0°C

System	Initial conc. of Na ⁺ ion solution (M)	Final conc. of Na ⁺ ion solution (M) C _{Na⁺}	Change in Na ⁺ ion conc. (M)	Conc. of H ⁺ ion exchanged (M) C _{H⁺}	Amount of Na ⁺ ions exchanged on the resin meq./0.500g C _{RNA}	Equilibrium constant K
1	0.010	0.005	0.005	0.005	0.245	0.075
2	0.020	0.012	0.008	0.008	0.400	0.090
3	0.025	0.016	0.009	0.009	0.465	0.095
4	0.030	0.029	0.011	0.011	0.505	0.059
5	0.040	0.028	0.012	0.012	0.590	0.089

Average equilibrium constant (K) = 0.081

Earlier researchers have expressed the concentration of ions in the solution in terms of molality and concentration of ions in resin in terms of mole fraction²³. In view of above, the experimental results obtained in the present study have been substituted in the following equation by Bonner et. al^{16, 20} and the equilibrium constant \mathcal{K}' was calculated (Table 2 and 4).

$$\mathcal{K}' = \frac{[N_{x^+}] [m_{H^+}]}{[N_{H^+}] [m_{x^+}]} \quad \dots(4)$$

Here N_{x^+} = Mole fraction of K⁺ or Na⁺ ions exchanged on the resin

m_{H^+} = Molality of H⁺ ions exchanged in the solution


N_{H^+} = Mole fraction of H⁺ ions remained on the resin

m_{x^+} = Molality of K⁺ or Na⁺ ions remained in the solution at equilibrium.

Since in the present study the solution was dilute, the molality and molarity of the ions in the solution were almost the same, with negligible error. Therefore, the molality of the ions can be easily replaced by molarity. The equilibrium constant \mathcal{K}' was calculated by equation 4 and the average value of \mathcal{K}' is reported (Tables 2 and 4). Such \mathcal{K}' values were

calculated for different temperatures and the values were in good agreement with \mathcal{K} values calculated by equation (3) (Table 5). This justifies that the choice of units for the concentration in the present study is insignificant. The enthalpy value for the ion exchange reactions (1) and (2) were calculated by plotting the graph of $\log \mathcal{K}$ against $1 / T$ ^{25, 27}. Bonner and Pruet¹⁶ studied the temperature effect on uni-univalent exchanges involving some bivalent ions. In all bivalent exchanges, the equilibrium constant decreases with rise in temperature resulting in exothermic reactions. However in the present investigation, the equilibrium constant \mathcal{K} increases with rise in temperature (Table 5), indicating the endothermic ion exchange reactions. The low enthalpy and higher \mathcal{K} values for H^+/K^+ exchange as compared to that for H^+ / Na^+ exchange (Table 3), indicate that the resins in H^+ form are having more affinity for larger ionic size K^+ ions in solution as compared to that for Na^+ ions also in the solution.

Table 4 : Equilibrium constant for the ion exchange reaction



Amount of the ion exchange resin in H^+ form = 0.500 g,

Ion exchange capacity = 3.38 meq. / g,

Volume of Na^+ ion solution = 80.0 mL,

Temperature = 30.0 °C

System	Initial conc. of Na^+ ions in solution (M)	Final conc. of Na^+ ions in solution (M) m_{Na^+}	Conc. of H^+ ions exchanged in solution (M) m_{H^+}	Mole fraction of Na^+ ions exchanged on the resin N_{Na^+}	Mole fraction of H^+ ions remained on the resin N_{H^+}	Equilibrium constant K'
1	0.010	0.005	0.005	0.075	0.925	0.087
2	0.020	0.012	0.008	0.090	0.910	0.117
3	0.025	0.016	0.009	0.095	0.915	0.113
4	0.030	0.029	0.011	0.089	0.911	0.094
5	0.040	0.028	0.012	0.059	0.941	0.089

Average equilibrium constant (K^{λ}) = 0.083

Table 5: Effect of temperature on equilibrium constant (K) for uni-univalent ion exchange reactions using ion exchange resin Indion-225Amount of the ion exchange resin in H^+ form = 0.500 g,Volume of K^+ / Na^+ ion solution = 80.0 mL

Ion exchange reactions	Equilibrium constant of ion exchange reaction	Temperature ($^{\circ}C$)			Enthalpy of the ion exchange reactions (kJ/mol)
		30.0	35.0	40.0	
$R-H + K^+(aq.)$ \updownarrow $R-K + H^+(aq.)$	K	0.100	0.128	0.147	13.2
	K'	0.100	0.128	0.147	
$R-H + Na^+(aq.)$ \updownarrow $R-Na + H^+(aq.)$	K	0.081	0.092	0.102	27.4
	K'	0.083	0.092	0.102	

REFERENCES

1. N. N. Andreev and Yu. I. Kuznetsov, *Russ. J. Phys. Chem.*, **64**, 1537 (1990).
2. A. Bhargava and C. Janardanan, *Indian J. Chem.*, **36A**, 624 (1997).
3. D. Muraviev, A. Gonzalo and M. Valiente, *Anal. Chem.*, **67**, 3028 (1995).
4. G. E. Boyd, F. Vaslow and S. Lindenbaum, *J. Phys. Chem.*, **71**, 2214 (1967).
5. J. F. Duncan, *Aus. J. Chem. Soc.*, **8**, 1 (1955).
6. G. E. Boyd, F. Vaslow and S. Lindenbaum, *J. Phys. Chem.*, **68**, 590 (1964).
7. A. Schwarz and G. E. Boyd, *J. Phys. Chem.*, **69**, 4268 (1965).
8. N. I. Gamayunov, *Russ. J. Phys. Chem.*, **64**, 1787 (1990).

9. G. E. Boyd and G. E. Myers, *J. Phys. Chem.*, **60**, 521 (1956).
10. O. D. Bonner, *J. Phys. Chem.*, **59**, 719 (1955).
11. O. D. Bonner, *J. Phys. Chem.*, **58**, 318 (1954).
12. S. Lindenbaum, C. F. Jumper and G. E. Boyd, *J. Phys. Chem.*, **63**, 1924 (1959).
13. K. A. Kraus and R. J. Raridon, *J. Phys. Chem.*, **63**, 1901 (1959).
14. O. D. Bonner and W. H. Payne, *J. Phys. Chem.*, **58**, 183 (1954).
15. W. J. Argersinger and A. W. Davidson, *J. Phys. Chem.*, **56**, 92 (1952).
16. O. D. Bonner and R. R. Pruett, *J. Phys. Chem.*, **63**, 1420 (1959).
17. O. D. Bonner and F. L. Livingston, *J. Phys. Chem.*, **60**, 530 (1956).
18. O. D. Bonner and L. L. Smith, *J. Phys. Chem.*, **61**, 326 (1957).
19. O. D. Bonner and C. F. Jumper and O. C. Rogers, *J. Phys. Chem.*, **62**, 250 (1958).
20. O. D. Bonner and L. L. Smith, *J. Phys. Chem.*, **61**, 1614 (1957).
21. J. Kielland, *J. Soc. Chem., Ind. (London)* **54**, 232 (1935).
22. A. P. Vanselow, *J. Am. Chem., Soc.* **54**, 1307 (1932).
23. G. L. Gaines (Jr.) and H. C. Thomas, *J. Chem. Phys.*, **21**, 714 (1953).
24. K. A. Kraus, R. J. Raridon and D. L. Holcomb, *Chromatogr. J.*, **3**, 178 (1960).
25. R. S. Lokhande, P. U. Singare and A. B. Patil, *Russ. J. Phys. Chem., A*, **81**, 2059 (2007)
26. P. U. Singare, R. S. Lokhande and T. S. Prabhavalkar, *Bull. Chem. Soc. Ethiop.*, (2008) (in Press)
27. R. S. Lokhande and P. U. Singare, *J. Ind. Council Chem.*, **24**, 73 (2007)
28. R. S. Lokhande, P. U. Singare and A. R. Kolte, *Bull. Chem. Soc. Ethiop.*, **22**, 107 (2008).
29. R. S. Lokhande, P. U. Singare, S. A. Parab, M. H. Dole, A. R. Kolte and P. Karthikeyan, *Int. J. Chem. Sci.*, (In press) (2008)
30. O. D. Bonner, G. Dickel, H. Brummer and *Z. Physik. Chem., (Frankfurt)*, **25**, 81 (1960).
31. G. L. Starobinet, V. S. Soldatov and A. A. Krylova, *Russ. J. Phys. Chem.*, **41**, 194 (1967).
32. R. S. Lokhande, P. U. Singare and A. B. Patil, *Radiochim. Acta*, **95**, 111 (2007).

33. R. S. Lokhande and P. U. Singare, *Radiochim. Acta*, **95**, 173 (2007).
34. R. S. Lokhande, P. U. Singare and A. R. Kolte, *Radiochim. Acta*, **95**, 595 (2007)
35. R. S. Lokhande, P. U. Singare and M. H. Dole, *J. Nucl. Radiochem. Sci.*, **7**, 29 (2006)
36. R. S. Lokhande and P. U. Singare, *J. Porous Mater*, **15**, 253 (2008)
37. R. S. Lokhande, P. U. Singare and P. Karthikeyan, *Russ. J. Phys. Chem., A*, **81**, 1768 (2007)
38. R. S. Lokhande, P. U. Singare and M. H. Dole, *Radiochemistry*, **49**, 519 (2007).
39. P. U. Singare, R. S. Lokhande and A. B. Patil, *Radiochim. Acta*, **96**, 99 (2008).
40. R. S. Lokhande, P. U. Singare and S. R. D. Tiwari, *Radiochemistry*, (2008) (in press).
41. R. S. Lokhande, P. U. Singare and T. S. Prabhavalkar, *Russ. J. Phys. Chem., A*, **82**, 1589 (2008).
42. R. S. Lokhande, P. U. Singare and S. A. Parab., *Radiochemistry*, (2008) (in press).
43. R. S. Lokhande, P. U. Singare and V. V. Patil, *Radiochemistry*, (2008) (in press).
44. R. S. Lokhande, P. U. Singare and S. R. D. Tiwari, *Russ. J. Phys. Chem., A*, (2009) (in press).

Accepted : 05.03.2009